



ResiDUAL[®]

DUAL RESIN JOINTING COMPOUND

Installation Guide

www.resiply.co.uk

ResiDUAL[®]

DUAL RESIN JOINTING COMPOUND

MIXING INSTRUCTIONS



Remove all contents from the bucket. **Pour and mix thoroughly** part **A+B** into the bucket using a paddle whisk.

1



Add **3/4 water** to the empty resin bottle and mix again thoroughly. Add a little more water if needed.

2



Open the bag of sand and **empty all of the contents** into the resin and water mix bucket.

3



Mix for the final time in a **circular and up and down motion** until the contents are fully mixed.

4

APPLICATION INSTRUCTIONS



Clean the whole area to be pointed and **dampen the surface** then empty the compound on to the wet surface.

5




Using a **stiff nylon brush** apply the compound over the whole surface of the area being jointed.

6



Once the water has been slightly evaporated, it is ready for a final **light brushing** to remove all the sand grains.

7



Keep off until the compound has fully dried
***See weather instructions.**

8



This is **NOT** an all weather product and should not be used if heavy or persistent rain is forecast. Never lay coverings directly on the surface.

Elevate the coverings and leave an air tunnel vent if possible.



Hot weather conditions will **not** damage this product but will reduce the drytime so don't leave too long before doing a final brush off.

Working time: 20 mins - 20°C



Cold weather conditions will **reduce** the drytime and leave the product open to the elements for a longer period of time, increasing the risk of permanently damaging the compound.

Do not use in temperatures less than 5°C we advise the buckets to be stored in a warm place prior to use and use warm water maximum 1 empty resin bottle.



ResiDual will give a **temporary** colour enhancement to most products however, it only lasts **1-2 months** from application. Sealers can be used before or after the application of ResiDual, but we strongly recommend a patch test first.

Never use acids or acidic cleaners on this product to avoid adverse reactions.
Never add colour dyes with this product.

M²

This is **20KG** bucket as an average guide will joint an area of between **10 - 11m²** of mixed size paving slabs. Joint width **10mm** and depth **30mm**.

*Approximate guide only

TOOLS FOR THE JOB



GLOVES AND GOGGLES SHOULD BE WORN AT ALL TIMES

